

**TECHNICAL FILE**

application: premium flat 200 mm      date: 5/02/2024  
P2730 foiled/mass coloured      version: v2



			EN 13245-2:2008/AC:2009	EN 13245-3:2010	based on	specific property	unit	value
MATERIAL CHARACTERISTICS	physical properties	density (co-extruded profile); not foiled	---	---	ISO 1183-1/A		kg/dm <sup>3</sup>	0,90 ± 0,05
	thermal properties	linear thermal expansion (-20 °C ... +60°C)	---	---	internal test method		mm/m.°C	0,05
		vicat softening point (hard PVC-U top layer)	---	---	ISO 306/B50		°C	≥ 75
PRODUCT CHARACTERISTICS	mechanical properties	impact resistance (23 °C)	§ 4.3	§ 5.4	EN 477 / EN 13245-3:2010 Annex B	falling mass	(T, J)	(23, 20)
	durability	natural weathering (2 GJ/m <sup>2</sup> )	§ 4.4	§ 5.5	Bandol	charpy impact strength retention	%	≥ 50
		artificial weathering (8 GJ/m <sup>2</sup> ; 300-800 nm)	---	§ 5.5	EN 513 method 1	code	class	N.2.23
		artificial weathering (8 GJ/m <sup>2</sup> ; 300-800 nm)	---	§ 5.5/6.4	EN 513 method 1	change in colour; grey scale ISO 105/A03; cleaned surface	grade	≥ 4 (foiled profiles); ≥ 2/3 (mass coloured profiles)
	thermal properties	heat reversion (75 °C)	---	§ 5.3	EN 479	adhesion foil (peel strength)	N/mm	≥ 2
		thermal resistance	---	§ 6.2	EN 478		%	≤ 1 (Code 1)
		single flame source	§ 4.1	---	ISO 11925-2	24 h / 70 °C		no bubbles, blistering, cracking or delamination
		single burning item	§ 4.1	---	EN 13823	classification EN 13501-1	class	E
					classification EN 13501-1	class	---	

*The test results relate only to a sample used by the Deceuninck laboratories. Whilst the Deceuninck laboratories warrant that their tests will meet their applicable declared specifications, the Deceuninck laboratories make no other warranty, expressed or implied and accept no responsibility or liability in respect of false results which are within the limits of the declared specifications of the tests offered. No representation or warranty is given by Deceuninck or any of its officers or employees as to the accuracy of any test methods or test results. Neither Deceuninck nor any of its officers or employees shall have any liability or responsibility in respect of any laboratory or the accuracy of any test methods, test results or reports produced by any Deceuninck laboratory.*