

TECHNICAL FILE TWINSON

application: O-Wall
P9576

date: 25/09/2024
version: v5



		EN 15534-1	based on	specific property	unit	value	
MATERIAL CHARACTERISTICS	physical properties	density	§ 6.2	ISO 1183-1/A		kg/dm ³	1.485 ± 0.050
	mechanical properties	flexural properties	§ 7.3.1	ISO 178	flexural modulus	MPa	5000 ± 10%
		flexural properties			bending strength	MPa	> 55
	durability	swelling and water absorption (28 days)	§ 8.3.1	EN 317	mass increase	%	< 8
		resistance to termites	§ 8.4	EN 117		class	1
		resistance against basidiomycetes	§ 8.5.2	ENV 12038		class	1
		resistance against soft rotting micro-fungi	§ 8.5.3	CEN/TS 15083-2		class	1
	thermal properties	linear thermal expansion (-20 °C ... +60°C)	§ 9.2	ISO 11359-2	length direction	10 ⁻⁶ K ⁻¹	20 - 25
		oxygen index	§ 10.1	ISO 4589-2		%	> 20
	PRODUCT RELATED CHARACTERISTICS	durability	natural weathering (1 year Bandol)			bending strength retention	%
boiling test			§ 8.3.3	ISO 1087-1	mass increase	%	< 8
thermal properties		heat reversion	§ 9.3	EN 479		%	< 0.2
		heat build-up	§ 9.4	ASTM D4803		°C	< 40
		single flame source	§ 9.6.1	ISO 11925-2	classification EN 13501-1	class	E

The test results relate only to a sample used by the Deceuninck laboratories. Whilst the Deceuninck laboratories warrant that their tests will meet their applicable declared specifications, the Deceuninck laboratories make no other warranty, expressed or implied and accept no responsibility or liability in respect of false results which are within the limits of the declared specifications of the tests offered. No representation or warranty is given by Deceuninck or any of its officers or employees as to the accuracy of any test methods or test results. Neither Deceuninck nor any of its officers or employees shall have any liability or responsibility in respect of any laboratory or the accuracy of any test methods, test results or reports produced by any Deceuninck laboratory.